


Aluminum Oxide Powder – 602

Specifications

Formula	$Al_2O_3^{101.96}$
Purity	99.99 %
Particle Size	-44/+10 Micron
CAS	1344-28-1
Melting Point	2072 °C
Boiling Point	2980 °C
Density	3.965 G/Cm ³
Mohs Hardness @ 20°C	9
Electric Resistivity	1×10^{22} Microhm-Cm
Crystal Structure	Hexagonal
Applications	Abrasives Lapping Polishing
MSDS	aluminum-oxide-powder-602-603-604-605-610-612-MSDS(PDF) aluminum-oxide-powder-602-603-604-605-610-612-MSDS(DOC)
Typical Analysis	aluminum-oxide-powder-602-Typical-Analysis
Form	Powder

Cost Per Kilogram

1-2 KG	
3-10 KG	
11-25 KG	
26+ KG	